



Datenblatt | Data Sheet

Übersicht | Overview

**KrampeHarex® Glasfaser | glass fibre**

Bezeichnung Name	Länge Length (mm)	Durchmesser Diameter ( $\mu\text{m}$ )	Querschnitt Cross section	Form Shape	Material Material	Werkstoff-Nr. Material-No.	Zugfestigkeit Tensile strength (N/mm <sup>2</sup> )
G 12/14 E	12 $\pm$ 10%	0,14 $\pm$ 10%	rund round	—	E-Glas E-Glass		3400 $\pm$ 15%
G 12/14 A	12 $\pm$ 10%	0,14 $\pm$ 10%	rund round	—	E-Glas E-Glass		3400 $\pm$ 15%

KrampeHarex® GmbH & Co. KG · Pferdekamp 6-8 · 59075 Hamm · Germany  
 Phone +49 (0)23 81 . 977 977 · Fax +49 (0) 23 81 . 977 955 · www.krampeharex.com · info@krampeharex.com

KrampeHarex® CZ s.r.o. · Blatného 12 · 61600 Brno · Czech Republic  
 Phone +42 (0) 541 . 247 773 · Fax +42 (0) 0541 . 247 817 · www.krampeharex.cz · info@krampeharex.cz

KrampeHarex® Fibrin Gesellschaft mbH & Co. KG · Lindengasse 20 · 4040 Linz · Austria  
 Phone +43 (0) 732 731 011 · Fax +43 (0) 732 . 731 011 73 · www.krampefibrin.com · info@krampefibrin.com