



Datenblatt | Data Sheet

Übersicht | Overview

KrampeHarex® gerade Stahldrahtfaser | straight steel wire fibre

Bezeichnung Name	Länge Length (mm)	Durchmesser Diameter (mm)	Querschnitt Cross section	Form Shape	Material Material	Werkstoff-Nr. Material-No.	Zugfestigkeit Tensile strength (N/mm ²)
DG 12,5/0,4	12,5 ±10%	0,40 ±10%	rund round	—	> C9D		> 1250 ±15%
DG 16/0,4	16 ±10%	0,40 ±10%	rund round	—	> C9D		> 1250 ±15%
DG 25/0,4	25 ±10%	0,40 ±10%	rund round	—	> C9D		> 1250 ±15%

KrampeHarex® GmbH & Co. KG · Pferdekamp 6-8 · 59075 Hamm · Germany
 Phone +49 (0)23 81 · 977 977 · Fax +49 (0) 23 81 · 977 955 · www.krampeharex.com · info@krampeharex.com

KrampeHarex® CZ s.r.o. · Blatného 12 · 61600 Brno · Czech Republic
 Phone +42 (0) 541 · 247 773 · Fax +42 (0) 0541 · 247 817 · www.krampeharex.cz · info@krampeharex.cz

KrampeHarex® Fibrin Gesellschaft mbH & Co. KG · Lindengasse 20 · 4040 Linz · Austria
 Phone +43 (0) 732 731 011 · Fax +43 (0) 732 · 731 011 73 · www.krampefibrin.com · info@krampefibrin.com