




KRAMPE HAREX®

KNOW WHY.

Data Sheet | Fibres

Version 01/2022

MELT EXTRACT FIBRE



GEOMETRY

① Type of fibre	melt extract fibres
② Shape of fibre	
③ Length	25 mm ± 10 %
Cross section	arched

FIBRE NETWORK

Quantity of fibres	25,800 fibre/kg
--------------------	-----------------

MATERIAL NUMBER & KH-CODE

DIN	1,4301
AISI	E304
④ KH-Code	4301

CERTIFICATIONS & SYSTEM APPROVALS

Certifications (DIN)	EN ISO 9001:2015, EN ISO 50001
----------------------	--------------------------------



MATERIAL PROPERTIES

Material	stainless steel
----------	-----------------

TEMPERATURE CHARACTERISTICS

Periodic operation	870 °C
Continous operation	980 °C
Melting temperature	1450 °C

CHEMICAL ANALYSIS

Carbon C	0.07 %
Manganese Mn	2.0 %
Phosphor P	0.045 %
Sulphur S	0.015 %
Chrome Cr	18.0-20.0 %
Nickel Ni	8.0-11.0 %
Aluminium Al	0 %
Silicon SI	1.0 %
Nitrogen N	0.11 %

Subject to change without notice. All specifications are only a general description of our products.

INFO

KrampeHarex® fibres are a cost effective solution:

- > Iron and steel industry
- > Petrochemical industry / Energy development
- > Cement and chalk industry
- > Waste incineration plants

In relation to our Service+ offer, we determine the suitable type of fibre, the optimal dosage and the necessary concrete strength. Further information can be found on our website krampeharex.com.

PACKAGING



Bags



Boxes



Big Bag

STORAGE



Keep Dry