



KRAMPE HAREX®

KNOW WHY.

Datasheet | Abrasives

Version 01/2025

BLASTEX BS CARBON STEEL CUT WIRE SHOT FOLLOWING DIN

GENERAL INFORMATION

Abrasive	Carbon steel cut wire shot
Shape	Cylindrical

SIZES

0.40 mm	1.20 mm
0.50 mm	1.40 mm
0.60 mm	1.60 mm
0.70 mm	1.80 mm
0.80 mm	2.00 mm
0.90 mm	2.20 mm
1.00 mm	2.40 mm

PHYSICAL PROPERTIES

Hardness	Alloy dependent	
Specific weight	8,4 g/cm ³	Alloy-dependent
Bulk weight	5,3 kg/l	

MODE OF USE

Reusable blasting medium

CHEMICAL COMPOSITION

C	min. 0.85 %	S	max. 0.05 %
Si	min. 0.40 %	P	max. 0.05 %
Mn	0.60 – 1.20 %		

PHYSICAL PROPERTIES

Blast cleaning	Deburring
Descaling	

SHOT BLASTING SYSTEMS

Blasting wheel, (compressed air)

CERTIFICATIONS & SYSTEM APPROVAL

Standards (Works standard)	Following DIN 8201-4
Certifications (DIN)	ISO 9001, ISO 50 001



Subject to change without notice. All specification are only a general description of our products. For detailed information please ask for our product leaflets.

INFO

Conditioned carbon steel cut wire shot for blast cleaning is made from stainless steel wire of selected diameter and tensile strength by means of special cutting machines. If required (e.g. initial filling of the blasting system), the steel wire grain can be rounded subsequently.

PACKAGING



Bags
25 kg
1000 kg Palett



Big Bag
1000 kg Palett

STORAGE



Keep Dry

