



KRAMPE HAREX®

KNOW WHY.

Data Sheet | Fibres

Version 05/2019

WIRE FIBRE STRAIGHT STEEL FIBRES

- 1 Type of fibre
- 3 Length
- 5 Material Specification

DG 20/0,30

- 2 Shape of fibre
- 4 Diameter



GEOMETRY

1 Type of fibre	wire fibre
2 Shape of fibre	Straight steel fibres
3 Length (L)	20 mm ± 10%
4 Diameter (d)	0,30 mm ± 10%
Cross section	round
Ratio (L/d)	67

FIBRE NETWORK

Quantity of fibres	90.100 fibres/kg
Minimum dosage	-

MATERIAL PROPERTIES

5 Material specifications	Normal tensile strength
Material	Steel
Material number	1.0620, 1.0622, 1.0626, 1.0616, 1.0628, 1.0618
Tensile strength	≥ 2.100 N/mm ²
Modulus of elasticity	210.000 N/mm ²

CERTIFICATIONS & SYSTEM APPROVALS

Standards (DIN)	EN 14889-1
Certifications (DIN)	EN ISO 9001:2015, EN ISO 50001



Subject to change without notice. All specifications are only a general description of our products. For detailed information please ask for our product leaflets.

INFO

Krampe Harex® Fibres are a cost effective solution to conventional reinforcement methods.:

- > Industrial floors
- > Tunneling applications
- > Precast concrete elements
- > Applications in residential buildings

In relation to our **Service+** offer, we determine the suitable type of fibre, the optimal dosage and the necessary concrete strength. Further information can be found on our website krampeharex.com.

PACKAGING



Bags



Boxes*



Big Bag



Keep Dry

* Fibres are magnetically linearized.